Report Number : **SINT22811589-REV2**



SINT22811589
ORIGINAL

Intertek Testing Services (Singapore) Pte Ltd.
5 Pereira Road, #06-03 Asiawide Industrial Building, Singapore 368025
Tel:(65) 6388 8666 Fax:(65) 6382 6268 E-mail address:singapore.softlines@intertek.com; RCB Reg No. 197401138D
The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Attention is drawn to the terms and condition for testing printed overleaf

intertek
Total Quality. Assured.

TEST REPORT

NUMBER : SINT22811589-REV2
DATE : 26-Jan-2023

APPLICANT : **Jiangsu Sidefu Textile Co Ltd**
No52 YongXing Road Nantong Jiangsu P.R. of China, Jiangsu, China (Mainland)
ATTN : **Lily Wei**

THIS IS TO SUPERSEDE REPORT NO. SINT22811589-REV1 DATED 06-Jan-2023

Sample Description	: Bath Mat For Doubletree/Hilton/Emabssy Suites/Home2 Suites/Hampton/HGI/Curio/Tapestry 50*85cm 775gsm 100% Cotton 12s/2*21s/2*16s/1
Fabric Weight	: 775gsm
Fiber Content	: 100% Cotton
Construction	: 12s/2*21s/2*16s/1 50*85cm
Color	: White
End Product	: Men/Women
Buyer	: Hilton World
Purchase Order No.	: -
Article No	: -
Style No	: -
Manufacturer	: Jiangsu Sidefu Textile co., Ltd

Applicant Provided Care Instructions :



Date Received/Date Test Started : 03 Jan 2023

FOR Intertek Testing Services (Singapore) Pte Ltd.
[Singapore]

DR.CHEN HUAYI
ASSISTANT GENERAL MANAGER

Intertek Testing Services (Singapore) Pte Ltd.
5 Pereira Road, #06-03 Asiawide Industrial Building, Singapore 368025
Tel:(65) 6388 8666 Fax:(65) 6382 6268 E-mail address:singapore.softlines@intertek.com; RCB Reg No. 197401138D
The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Attention is drawn to the terms and condition for testing printed overleaf

TEST REPORT

NUMBER : SINT22811589-REV2
DATE : 26-Jan-2023

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Color Evaluation
(ISO 105-J03: 2009)

Whiteness CIE/WI	154.65

2. Dimensional Stability To Washing
(ISO 3759-2011/ISO 5077-2008/ISO 6330-2021 Wascator Washing Machine-Front-Loading Horizontal Rotating Drum Type, Test Programme 4M, 40°C With 2 kg Total Load, In 20 g Non-Phosphate Reference Detergent 3, Followed By Tumble Dry Medium)

After Three Washes

Warp (%)	-2.2
Weft (%)	-1.6

REMARK:
(+)Means extension and (-)Means shrinkage.

3. Fiber Identification
ISO 1833 -_1_: 2020

Cotton (%)	100

4. Appearance After Wash
(BS EN ISO 6330 - 2021/ISO 3759: 2011/ 5077: 2007): [Wascator washing Machine-Front-Loading horizontal rotating drum type, test programme 4M at 40°C, 2 kg load, in 77% ECE reference detergent 3% Bleaching Activator (TAED) and 20% Sodium Perborate solution, followed by tumble dry Medium]

After Three Washes

Observation :

The sample looked satisfactory.
No obvious pilling was observed.

Intertek Testing Services (Singapore) Pte Ltd.
5 Pereira Road, #06-03 Asiawide Industrial Building, Singapore 368025
Tel:(65) 6388 8666 Fax:(65) 6382 6268 E-mail address:singapore.softlines@intertek.com; RCB Reg No. 197401138D
The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Attention is drawn to the terms and condition for testing printed overleaf

TEST REPORT

NUMBER : SINT22811589-REV2
DATE : 26-Jan-2023

5. Pile Height and Length

Visual Assessment - Standard Measure

(mm)	**3**

6. Counts Of Yarn

(ISO 7211-5: 2020)

Warp Yarn	
	21.6's/2 (27.3 tex)
Weft Yarn	
	15.4's/1 (38.4 tex)
Loop Yarn	
	12.3's/2 (47.9 tex)

REMARK:
's = English Cotton Count

7. Fabric Weight

(ISO 3801 : 1977)

(g/sq.m)	791.8
(oz/sq.yd)	23.4
(% Deviation)	2.2

8. Tensile Strength

(BS EN ISO 13934/1-2013 : 50mm Strip Test, Hounsfield/Instron, CRE)

Strength

Warp	40.8 kg
Weft	39.1 kg

Intertek Testing Services (Singapore) Pte Ltd.
5 Pereira Road, #06-03 Asiawide Industrial Building, Singapore 368025
Tel:(65) 6388 8666 Fax:(65) 6382 6268 E-mail address:singapore.softlines@intertek.com; RCB Reg No. 197401138D
The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Attention is drawn to the terms and condition for testing printed overleaf

9. Absorbency
(AATCC 79-2018)

(second)	1

END OF THE TEST REPORT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at http://www.intertek.com/terms.

Intertek Testing Services (Singapore) Pte Ltd.
5 Pereira Road, #06-03 Asiawide Industrial Building, Singapore 368025
Tel:(65) 6388 8666 Fax:(65) 6382 6268 E-mail address:singapore.softlines@intertek.com; RCB Reg No. 197401138D
The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Attention is drawn to the terms and condition for testing printed overleaf

TEST REPORT

NUMBER : SINT22811589-REV2
DATE : 26-Jan-2023

To : Jiangsu Sidefu Textile Co Ltd
No52 YongXing Road Nantong Jiangsu P.R. of China, Jiangsu, China (Mainland)

Attention : Lily Wei

Date : Jan 26, 2023

Re : Report Revision Notification

Report Number SINT22811589-REV1 date 06-Jan-2023

This report has been revised to amend Fiber, Pile Height and Yarn count tests.

Thank you for your attention.

For Intertek Testing Services (Singapore) Pte Ltd. [Singapore]

Dr.Chen Huayi
Assistant General Manager

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Attention is drawn to the terms and condition for testing printed overleaf